# Determination of the Size Effect Law with One-Size Concrete Specimens of Different Notch Depths

H. Cifuentes<sup>1</sup> and F. Medina<sup>2</sup>

## Summary

The most popular expression that considers the size effect showed in concrete structures is the size effect law of Bazant. This law depends on two coefficients  $G_f$  and  $c_f$ . For the experimental determination of these coefficients is necessary obtaining the ultimate loads, in three points bending tests, of notched beams with different sizes. In this work, a method to determine the coefficients about the results on identical beams varying the deep of the notch, is presented. The necessary values of loads are obtained by a numerical analysis with FEM that considers non linear behaviour of the concrete material. Next the proposed method is applied to experimental results of concrete specimens with different relative notch depth.

#### Introduction

The size effect in concrete structures can be considered by the size effect law of Bazant [1,2]. This law is defined by two coefficients,  $G_f$  and  $c_f$ , wich are considered as material's properties.

The experimental determination of these coefficients can be done by a procedure of the international association RILEM, which propose a three-point-bending tests of geometrically similar single edge notched bend (SENB) specimens of concrete with three different sizes.

To avoid the manufacturing of specimens of different sizes, a method is proposed in this work that allows the determination of these coefficients by means of the ultimate loads obtained in specimens of same size, but different notch depths.

A numerical and experimental application of the proposed method has been done in this work. The numerical studies have been realized with a FEM commercial program (ABAQUS) that allows obtains the peak load and softening curve of concrete specimens. For the experimental analysis, notched specimens of same size with different notch depth have been manufactured and tested.

## **Proposed Method**

The proposed method is based in the relation given by the size effect law of Bazant, between the nominal stress at failure and the geometry of specimens tested. The size effect law is:

$$\sigma_N = \frac{P_u}{BD} = \sqrt{\frac{EG_f}{g'(\alpha)c_f + g(\alpha)D}}$$
(1)

<sup>&</sup>lt;sup>1</sup>Grupo de Estructuras, Esc. Tec. Sup. de Ingenieros de Sevilla. Spain.

<sup>&</sup>lt;sup>2</sup>Grupo de Estructuras, Esc. Tec. Sup. de Ingenieros de Sevilla. Spain.

Where  $P_u$  is the ultimate load, B the thickness of the specimen, D a characteristic dimension (the depth is usually considered), E the elastic modulus of concrete,  $g(\alpha)$  and  $g'(\alpha) = dg(\alpha)/d\alpha$  functions of the specimen's geometry and the relative notch depth ( $\alpha = a/D$ ) and  $G_f$  and  $c_f$  asymptotic constants of concrete. These constants are defined as the specific fracture energy and the length of the fracture process zone for specimens of infinite size [1,2]. The coefficient  $g(\alpha)$  is related with the parameter  $Y(\alpha)$  used for the determination of  $K_{IC}$  [2].

From size effect (1) and with the obtained (numerical or experimental) values of  $\sigma_N$ , a relation between  $G_f$ ,  $c_f$  and  $y(\alpha) = 1/\sigma_N^2$  can be determined. The relation is obtained as follows:

$$G_f(\alpha) = \frac{g'(\alpha)c_f(\alpha) + Dg(\alpha)}{E_c y(\alpha)}$$
(2)

The plot of the relation given by equation (2) in a  $G_f - c_f$  axes for each relative notch depth, are straight lines that must be crossed in a single point. It will be able using this point to predict the  $G_f$  and  $c_f$  coefficients as properties of the material.

#### Numerical Studies with MEF

The determination of the ultimate loads in three-point-bending is necessary for the theoretic development of the proposed method. In the following paragraphs a numerical study about the quasibrittle materials models for concrete in commercial FEM software (ABAQUS) is presented.

One of the available models for concrete in ABAQUS is the Concrete Smeared Cracking model, which considers elasto-plastic compression behavior with flow rule and isotropic hardening, and cracking in tension by means of the softening response.

The ABAQUS modeled notched specimens have dimensions: B = 150mm, D = 150mm, L = 600mm, S = 450mm and relative notch depth of  $\alpha = 0.033 - 0.1 - 0.167 - 0.233 - 0.3 - 0.367 - 0.433$  and 0.5. The modeled concrete have compressive strength  $f_c = 25$  MPa, tensile strength  $f_{ct} = 3.16$ MPa, elastic modulus  $E_c = 27264$ MPa and fracture energy  $G_F = 75$ N/m.

In figure 1, the  $G_f - c_f$  relationships for the numerical results are showed.

It is observed from figure 1, that there isn't a common point that allows obtain the  $G_f$  and  $c_f$  material properties. Therefore, it should be derived that these coefficients cannot be considered properties of concrete.

With  $y(\alpha)$  and its derivative  $y'(\alpha)$  an expression of  $G_f$  and  $c_f$  for each  $\alpha$  can be determined. If this expressions are plot (figure 2) the variation of these coefficients respect to the relative notch depth can be observed.

However,  $\alpha = 0.033$  curve cross the other curves in a similar point, which can be used to obtain a mean coefficients  $\mathbf{G}_{fm} = 33.73$  N/m and  $\mathbf{c}_{fm} = 10.79$  mm. With



Figure 1:  $G_f$  and  $c_f$  relationships for numerical results



Figure 2: Variation of  $G_f$  and  $c_f$  with respect to  $\alpha$ 

these mean values of the coefficients and using equation (1), the nominal tension  $\sigma_N$  for other relative notch depths can be obtained. Figure 3 shows the  $\sigma_N - \alpha$  curves from equation (1) with the  $G_f$  and  $c_f$  coefficients obtained with the proposed method, and the numerical results.



Figure 3:  $\sigma_N - \alpha$  curves with numerical results

## **Experimental Studies**

Several concrete notched specimens have been made up, of same size and identical relative notch depths than numerical models. A three-point-bending test was applied to these specimens obtaining the maximum loads for each of them. Figure 4 shows a picture of the notched specimens tested and the load and support condition



for three-point-bending tests.

Figure 4: Notched specimen and three-point-bending test



Figure 5: Experimental and proposed method  $\sigma_N - \alpha$  curves

The concrete has a compressive strength of  $f_c = 31.9$  MPa, tensile strength  $f_{ct} = 1.94$ Mpa, elastic modulus  $E_c = 23466$  Mpa and maximum aggregate size of 12 mm.

Table 1 shows the mean values of maximum loads and nominal stress obtained for each relative notch depth.

	<b>T</b>				
α	$P_{u}$ (N)	$\sigma_{Nu}$ (MPa)	α	$P_{u}$ (N)	$\sigma_{Nu}$ (MPa)
0.033	15815	0.703	0.300	8635	0.384
0.100	13015	0.578	0.367	8075	0.359
0.167	12395	0.551	0.433	7165	0.318
0.233	10595	0.471	0.500	6135	0.273

Table 1: Mean experimental maximum loads and nominal stress

Applying the proposed method to the experimental results, a common point for all  $G_f - c_f$  relations cannot be obtained again, as in numerical results. So it confirms that  $G_f$  and  $c_f$  coefficients cannot be considered as material properties. Similar conclusions has been determinate for other authors (Karihaloo et als.) [5,6]. These coefficients depend on the depth of the notch and geometry of the specimens. Experimental mean values of the coefficients can be derived from the cross point of all curves with the corresponding one to  $\alpha = 0.033$ . The mean values of the coefficients so obtained are  $\mathbf{G}_{fm} = 47.78$ N/m and  $\mathbf{c}_{fm} = 32.27$ mm.

Using these experimental mean values into equation (1), it can be obtained the nominal stresses  $\sigma_N$  for other relatives notched depths. In figure 5,  $\sigma_N - \alpha$  curves for the experimental results and by size effect law with the coefficients obtained are showed.

## Conclusions

- 1. A method to determine the  $G_f$  and  $c_f$  coefficients of the size effect law of Bazant, from results on concrete specimens of same size and different relative notch depths is presented.
- 2. To obtain the  $G_f$  and  $c_f$  coefficients with the proposed method is necessary to obtain the ultimate load of relative notch depths lower than 0.1.
- 3. Mean values of the coefficients of the size effect law are obtained with numerical and experimental results. With these values the determination of the ultimate loads for other relative notch depths can be obtained.
- 4. Variations in the values of the  $G_f$  and  $c_f$  coefficients relative to the notch depth are showed. That concludes these coefficients should not be considered properties of the material.
- 5. The obtained results are not directly applicable to obtain the nominal stresses corresponding to specimens in different sizes, as derived from preceding conclusions.

## References

- 1. Bazant, Z.P. (2005): Scaling of Structural Strength, Elsevier.
- 2. Bazant, Z.P. and Planas, J. (1998): *Concrete and Size Effect in Concrete and Other Quasibrittle Materials*, CRC Press.
- 3. Cifuentes, H. and Medina, F. (2006): *El Efecto Tamaño en la Fractura del Hormigón Estructural. Estudio Numérico y Experimental sobre Probetas Entalladas*, Master Thesis, University of Seville.
- Hu, X. and Duan, K. (2007): "Size Effect: Influence of proximity of fracture process zone to specimen boundary", *Engineering Fracture Mechanics*, Vol. 74, pp. 1093-1100.
- 5. Karihaloo, B.L. and Abdalla, H.M. (2006): "Deterministic Size Effect in the Strength of Cracked Concrete Structures", *Cement and Concrete Research*, Vol. 36, pp. 171-188.
- Karihaloo, B.L. and Abdalla, H.M. (2003): "Size Effect in Concrete Beams", *Engineering Fracture Mechanics*, Vol. 70, pp. 979-993.

202 Copyright © 2008 ICCES

7. Shah, S.P. and Carpinteri, A. (1991): *Fracture Mechanics. Test Methods for Concrete. RILEM Report 5*, Chapman and Hall.